

ThermoSink 35-6

Technical Data Sheet

ThermoSink 35-6 is a two-component, thermally conductive silicone elastomer that cures rapidly at room temperature. ThermoSink 35-6 is designed for electrical potting and/or thermal interface applications where high-performance heat transfer and thermal management is required.

APPLICATIONS	FEATURES	SUBSTRATES
Automotive	Thermally Conductive	Engineered Plastics
Electronic Assembly	Water Resistant	Ceramics
Power Supplies	Fast set, Room-temperature Cure	Plastics
	RoHS Compliant (Pending)	Metals

Typical Properties of Uncured Material*

Chemical Class	2K Silicone
Color (Part A / Part B)	Grey / White
Viscosity, Part A @25°C, @10RPM, cps	35,000 to 55,000
Viscosity, Part B @25°C, @10RPM, cps	7,000 to 11,000
Viscosity, Mixed @25°C, @10RPM, cps	15,000 to 45,000
Mixed Specific Gravity	2.87
Mix Ratio, PBW (A:B)	50:50
Cleanup Solvent	Isopropyl alcohol
Standard Operating Temperature Range, °C	- 40 to 200

Cure Guidelines*

Set Time @ 25°C, minutes	30 to 60
Cure Time @ 25°C, hours	2
Cure Time @ 100°C, minutes	45

Typical Properties of Cured Material*

Durometer, Shore A	65-75
Young's Modulus (At room temperature), MPa	5.15
Glass Transition Temperature, °C	- 68
CTE, ppm, Above Tg	~ 120
Dielectric Constant, @ 1 MHz	7.4
Dielectric Strength, Volt/mil	250
Volumetric Resistivity, Ω*cm	1 * 10 ¹³
Dissipation Factor, @ 1 MHz	0.001
Thermal Conductivity, W/m °K	>3.5
Flammability, UL94**	V0

***All properties given are typical values and are not intended for use in preparing specifications.**

**** Flammability tested in-house with 3 mm thick sample using identical conditions as UL94 flame chamber**

Storage

Both Part A and Part B need to be thoroughly remixed individually prior to use. Keep stored between 8°C and 28°C in tightly closed, light-blocking containers away from direct sunlight. Keep from freezing Please refer to product labeling for shelf-life information. Consult SDS for safe handling recommendations.



RESIN DESIGNS MAKES NO EXPRESSED OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT. APPLICATION OF THIS MATERIAL SHOULD COMPLY WITH LOCAL AND NATIONAL HEALTH AND SAFETY REGULATIONS.

www.resindesigns.com

781-935-3133